

Independent Textile Testing Service, Inc.

Test No: 146848

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: Mannington Commercial

July 31, 2014

Subject: Sample(s) of carpet submitted for testing by the Customer and identified below:

Sample Identification: Style: Canopy II
Back: Infinity Modular

| |
|--|
| Test Method Conducted |
| ASTM D-5252 Hexapod Drum Tester |
| ISO/TR 10361 Hexapod Tumbler |
| Ratings Based on CRI TM-101 Photographic Scales |
| ASTM D-7330 Assessment of Surface Appearance Change in Pile Floor Coverings |

APPARATUS: WIRA INSTRUMENTATION HEXAPOD TUMBLER CARPET TESTER

PROCEDURE:

The test specimen described above was subjected to the reported cycles of "Hexapod" tumbling, removing the specimen every 2,000 cycles for restoration by vacuuming.

A 6.7 Amp Shark handheld vacuum w/rotary brush was used, making four (4) forward and backward passes along the length of the specimen.

The samples were assessed using day-light equivalent vertical lighting (1500 lux). Samples were viewed at an angle of 45 degrees from 1½ meter distance, judging from all directions.

TEST RESULTS:

| NUMBER OF HEXAPOD CYCLES | OVERALL APPEARANCE CHANGE |
|--------------------------|---------------------------|
| 12,000 | 3.5 |

| Key to Ratings |
|-----------------------------|
| 5 = Negligible or no change |
| 4 = Slight change |
| 3 = Moderate change |
| 2 = Considerable change |
| 1 = Severe change |

President L. Kent Suddeth