

TEST REPORT

CI.	IC	м	т.

Company:	Mannington Commercial	Report Number:	700011
Address:	PO Box 12281	Lab Test Numbers:	2886-1328
	Calhoun, GA 30703-7004	Test Completion Date:	2/3/2017
		Report Date:	2/16/2017
Requested By:	Ragan Hayes	Page:	1 of 1

TEST MATERIAL:

Material Type:	Carpet	Date Received: 1/20/2017
Material Condition:	EXCELLENT: XXX GOOD	POOR: REJECTED:
Style:	Montgomery	Hard State Control of the Control of
Backing:	Infinity Modular	

TESTING METHODS REQUESTED:

LESTING METH	ODS REQUESTED.		
R Designation	real of the second	esting Services Inc. was instruct	ed by the client to test for the following
Standard:	ASTM E648, NFPA 253		Standard Test Method for Critical Radiant Flux of Floor Covering Systems Using a
KEND OF SHE	FTM Standard 372	经企业企业 的企业的证据中央主	Radiant Heat Energy Source

SAMPLING PLAN:

Sampling Date: 1/20/2017

- Specimen sampling is performed in the sampling department at TSI beside the ground level dock door.
- The sampling size of specimens is determined by the test method requirements.
- In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager.
- All samples are subjected to the outside environmental conditions of temperature and relative humidly.
 - Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusion	s From Tes	st Metho	d.	
None				

TEST SCOPE:

This test method measures the critical radiant flux of horizontally mounted floor-covering systems exposed to a flaming ignition source positioned on a graded radiant heat energy environment within an enclosed chamber. The results are designed to provide a basis for estimating one aspect of fire behavior of a flooring system.

TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION		Burn Distance	TEST RESULT Time to Flame Out	Critical Radiant Flux
	311 15 11 15	0 1 94			0.75 W/m²
ASTM E648-15e1	Critical Radiant Flux	Specimen #1	27.4 cm	19:52 min	
		Specimen #2	29.2 cm	26:33 min	0.72 W/m ²
		Specimen #3	24.6 cm	22:11 min	0,80 W/m ²
A DOMESTICA SERVICES		Average		0.76 W/m²	
	NFPA Classification			Class I	Control of the Control
BEST CHEROSENSON DELENION	STDEV			0.04	
	COF of Variation			5.38 %	Continue to a light track of the

Mounting Board: Calcium Silicate Board Conditioning: 96 hours @ 70°F 50% RH

Adhesive: Infinity Calibration Curve: 355L Trowel: 1/16" X 1/16" X 1/16" U Notch

Radiometer #: 5356

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available.

TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests performed are in compliance with stated test method.

Test Report Approval:

Erle Miles, III, Lab Director, Testing Services Inc

tation: Our laboratory is accredited by the US Dept of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005.

Our code # is: NVLAP 100108-0.

Form:	Rev:	Revision Date:	Page 1 of 1	
Release Date:		Control Type: Electronic – Expires 24 hours		
	Printed copies are uncontrolled			

OUR LETTERS AND REPORTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. THESE LETTERS AND REPORTS ARE FOR THE USE ONLY OF THE CLIENT TO WHOM THEY ARE ADDRESSED AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME TESTING SERVICES, INC. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. OUR REPORTS, LETTERS, NAME, SEALS, OR INSIGNIA ARE NOT UNDER ANY CIRCUMSTANCES TO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.

PO Box 2041 Dalton, GA 30722-2041 (706) 226-1400 tsioffice@optilink.us