



Standard Carpets ind llc
P.O. Box No. 490014 Dubai Industrial Park
DUBAI
United Arab Emirates

Your notice of
05-05-2023

Your reference

Date
07-07-2023

Analysis Report 23.02615.01

Required tests :

AS ISO 9239-1 (2003)

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Sample id	Information given by the client	Date of receipt
T2311224	ON THE ROCKS (100% SOLUTION DYED NYLON CARPET TILE)	05-05-2023

Kristina De Temmerman
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2311224 - ON THE ROCKS (100% SOLUTION DYED NYLON CARPET TILE)

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	06-07-2023
Standard used	AS ISO 9239-1 (2003)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Fibre cement board - density (1800 ± 200) kg/m ³
Mounting	Loose-laid
Specimens have not been cleaned	
Joint	At 25 cm and 75 cm

Radiant heat flux

	Flame spread distance (cm)				Flame time	Heat flux kW/m²	
	10 min	20 min	30 min	Extin- guish- ment		30 min*	Extin- guishment**
Width							
#1	24	24	24	24	13 min 45 s	8.6	8.6
Length							
#1	24	24	24	24	14 min 33 s	8.6	8.6
#2	25	36	44	53	62 min 28 s	4.5	3.3
#3	24	24	24	24	17 min 40 s	8.6	8.6
Average						7.2	6.8

* Heat flux at the time of 30 minutes

** Heat flux at the time of flame extinguishment

Smoke production: Light attenuation

	Maximum (%)		Total (%.min)	
	30 min	Extin- guish- ment	30 min	Extin- guish- ment
Width				
#1	30	30	149	146
Length				
#1	24	24	131	129
#2	33	33	157	157
#3	26	26	135	133
Average			141	140