## WTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT : IRVINE FLOORING

PO BOX 16898 CHRISTCHURCH 8441

NEW ZEALAND

: 7-598421-CO TEST NUMBER : 16/07/2014 ISSUE DATE : 23/07/2014 PRINT DATE

SAMPLE DESCRIPTION Clients Ref: "Crazy XL"

Needle punch carpet

Colour; Grey

Approximate pile height: 6.2mm Nominal Composition: 100% Polypropylene Nominal Total Pile Mass: 760 g/m2

ISO 9239.1-2010 PART 1

Reaction to Fire Tests for Floorings Determination of the Burning Behaviour

Using a Radiant Heat Source

Date of sample arrival:

05/06/2014 14/07/2014

Date Tested:

Results:

CHF Values (Critical Heat Flux/Critical Radiant Flux)

Mean

Non-Directional

Non-Directional

5.3 5.3

6.5 5.7

kW/m2

Smoke Value 3 10 14

Mean 15

%.min

Observations: Melting, Blistering

20

Note: Sample was conditioned in accordance with BS EN 13238:2001 at a temperature of 23+/-2degC and relative humidity of 50+/-5% for a minimum of 48 hours prior to testing.

No directional properties, three specimens tested only

Each specimen was adhered to a substrate of 6mm fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

END OF REPORT

PAGE 1

© Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

207557



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
-Chemical Testing of Textiles & Related Products : Accreditation No. 983
-Mechanical Testing of Textiles & Related Products : Accreditation No. 985
-Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if ammended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

APPROVED SIGNATORY

HAEL A. JACKSON B.Sc.(Hons)

LIMITE