## Callisto

## **Belgotex**<sup>®</sup>



















Underfloor Heating

Ouick & Easy

Easy Clean

Construction	Heterogeneous Sheet Vinyl
Width	2.0m, 3.0m
Standard Roll Length	35m
Pattern Repeat	Refer to Vinyl Range Statement
Total Weight	1350g/m²
Wearlayer Thickness	0.2mm
Total Thickness	1.9mm
Slip Resistance	DS (DIN 51130)
Electrical Properties	Antistatic
Electrical Propensity	<2kV (EN 1815)
Fire Rating	ISO 9239-1
Dimensional Stability	0.4% (EN ISO 23999)
Volatile Organic Compounds	0.34 mg/m3 (EN 16516)
Indoor Air Quality	A+ Emissions
Residual Indentation	≤ 0.35mm (EN ISO 24343-1)
Underfloor Heating	Suitable up to 27°C
Chemical Resistance	Resistant (EN ISO 26987)
Abrasion Group	Class T (EN 651)
Classification	Class 21 Domestic Light
Warranty	5 Year Residential Warranty
Environmental	REACH Certificate of Compliance ISO 9001
Installation	Please contact Gilt Edge Industries for all adhesive and installation instructions. NB: If recommended adhesive is not used, claims will not be accepted. Must be laid in accordance with AS/NZ Installation Standards.

- For samples, range and warranty details please contact us on 0800 377 753 or belgotex.co.nz
- Specifications are based on averages from manufacturing processes and may vary within normal industry tolerances.
- This product is intended for use solely as an indoor floor covering and is not recommended or sold for any other purpose.
- Use entryway systems outside each entrance to prevent dirt, sand, grit and other substances from being tracked onto floor.
- Rubber Migration: Rubber migration (also known as Plasticiser Migration) is a condition that can cause vinyl to discolour. It is caused by rubber or latex products, eg rubber or latex-soled slippers, shoes and rubber backed mats, coming to contact with the vinyl over a constant period of time. It is neither a manufacturing nor an installation fault and therefore is not covered by our warranties.
- Plain, granite or patterned vinyls will either need to be reverse laid or a wider width should be used to allow for colour inequality, an additional allowance may have to be made for the pattern repeat.

