



(Please quote this number in all correspondence)

CLIENT: Belgotex 25 Leslie Hills Drive	SAMPLE RECEIVED FROM: Belgotex	Date Received:	5.9.22
Riccarton, Christchurch	SAMPLE DESCRIPTION:		
Attn.: Glen Ellis	LVT flooring samples glued down to Pers	spex base using	
	Range – Ultimo II		
	Colour – Summer Oak 24219		
Client Order No.:	Client Reference:		1 of 5

ISO 4760:2022(E) - LAMINATE FLOORING – TOPICAL MOISTURE RESISTANCE – ASSEMBLED JOINT (MODIFIED)

Method

The sample was cut into pieces then connected using the profiled locking edges and fastened into an assembled floating "T joint" configuration as per the test method. The testing was performed in triplicate.

Weights were not used on these samples.

100 mls of dye solution was applied onto the sample surface. It was poured into a cylinder 100mm diameter placed in the centre of the sample at the "T joint." Sealant was used at the plank/cylinder interface to avoid leakage.

The sample was left at 20°C, 65% Relative Humidity room conditions for 24 hours after the dye was added and then examined for dye penetration through the backing (not 23°C, 50% RH as stated in the method).

If swelling measurements are requested, thickness measurements are taken at specified test positions - before water, within 15 minutes after water removal (qualitative and quantitative) and 24 hours after removal of water (qualitative).

Quantitative measurements are used to calculate surface swell in mm (within 15 minutes after water removal) and recovery swell (24 hours after removal of water).

Date Tested: 12/9/2022

Note: Samples were assembled/glued down to Perspex by client.

Results:

Quantitative Results:	Wet Swell (mm)			Recovered Swell (mm)		
	Specimen 1	Specimen 2	Specimen 3	Specimen 1	Specimen 2	Specimen 3
Final Average (Positions 2 to 4)	0.00	0.00	0.00	0.00	0.00	0.00
Final average (Position 1)	0.00	0.00	0.00	0.00	0.00	0.00

	Wet Swell			Recovered Swell		
	Specimen 1	Specimen 2	Specimen 3	Specimen 1	Specimen 2	Specimen 3
Qualitative Ratings (individual results):	1	1	1	1	1	1

Qualitative Grade:

1 = No change - Little to no noticeable change in edge swell or panel surface lift

2 = Slight swelling - Slight swelling, small ridge along one or more joints, very little if any panel surface lift

3 = Moderate - Noticeable edge swelling and some panel surface lift extending away from joint

4 = Objectional - Severely raise edge and swelling extending noticeably under the panel surface

5 = Failed test - Water leaked out of the ring, leaving no continuous film of water inside the ring

(this grade is given even if there is no swell of the edge joint)

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED" Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION 0NLY. This document shall not be reproduced except in full.

Kev Technical Person





(Please quote this number in all correspondence)

CLIENT: Belgotex 25 Leslie Hills Drive	SAMPLE RECEIVED FROM: Belgotex	Date Received:	5.9.22
Riccarton, Christchurch	SAMPLE DESCRIPTION:		
	LVT flooring samples glued down to Persp	ex base using	
Attn.: Glen Ellis	UZIN KE 68 T adhesive.	C C	
	Range – Ultimo II		
	Colour – Summer Oak 24219		
Client Order No .:	Client Reference:		2 of 5

	Wet Swell			
	Specimen 1	Specimen 2	Specimen 3	
Observations:	No evidence of water penetrating the underside of the flooring planks through the joints.	No evidence of water penetrating the underside of the flooring planks through the joints.	Water was able to channel through the joints and puddle on the surface of the planks. There was water left inside the ring. Water penetrated to the Perspex base along the joints.	

		Recovered Swell			
	Specimen 1	Specimen 2	Specimen 3		
Observations:	No evidence of water penetrating the underside of	No evidence of water penetrating the underside of	Water penetrated to the Perspex base along the joints.		
	the flooring planks through the	the flooring planks through the	r erspex base along the joints.		
	joints.	joints.			

Note: The Acceptable Solutions and verification methods, New Zealand Building Code E3 Internal Moisture defines on page 9 definitions - "Impervious" - that which does not allow the passage of moisture. While E3.3.3 and E3.3.6 require impervious surfaces about sanitary appliances/fixtures, the impervious performance criteria compliance covered in Page 11 mentions "No specific methods have been adopted for verifying compliance with the performance of NZBC E3." In summary, the Objective (3.1) and Functional requirement (3.2) of E3 is to prevent illness/injury or damage through accumulation of moisture, or damage caused by free water penetration.

This ISO test method is used internationally and has been independently performed in New Zealand. The result of this test verified that this product's assembled joint over a 24 hour period did not allow water penetration through to the substrate, or if tested at the edges where edge sealant has been applied.

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED" Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION 0NLY. This document shall not be reproduced except in full.

Key Technical Person





(Please quote this number in all correspondence)

CLIENT: Belgotex 25 Leslie Hills Drive Riccarton, Christchurch

Attn.: Glen Ellis

SAMPLE RECEIVED FROM: Belgotex Date Received: 5.9.22

SAMPLE DESCRIPTION: LVT flooring samples glued down to Perspex base using UZIN KE 68 T adhesive. Range – Ultimo II Colour – Summer Oak 24219

Client Order No.:

Client Reference:



24 Hrs with Water



Water was able to channel through the joints and puddle on the surface of the planks.



Wet Swell

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED" Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.



Recovered Swell a Judan C Key Technical Person

16/09/2022

3 of 5





Date Received: 5.9.22

(Please quote this number in all correspondence)

CLIENT: Belgotex 25 Leslie Hills Drive Riccarton, Christchurch

Attn.: Glen Ellis


Client Order No.:

SAMPLE RECEIVED FROM: Belgotex

SAMPLE DESCRIPTION: LVT flooring samples glued down to Perspex base using UZIN KE 68 T adhesive. Range – Ultimo II Colour – Summer Oak 24219

Client Reference:

4 of 5



Water penetrated to the Perspex base along the joints.

"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED" Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION 0NLY. This document shall not be reproduced except in full.

C Judan Key Technical Person





Date Received: 5.9.22

(Please quote this number in all correspondence)

CLIENT: Belgotex 25 Leslie Hills Drive Riccarton, Christchurch

Attn.: Glen Ellis

Client Order No.:

SAMPLE RECEIVED FROM: Belgotex

SAMPLE DESCRIPTION: LVT flooring samples glued down to Perspex base using UZIN KE 68 T adhesive. Range – Ultimo II Colour – Summer Oak 24219

Client Reference:

5 of 5



"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED" Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION 0NLY. This document shall not be reproduced except in full.

udan

C Judan Key Technical Person