



Standard Carpets ind Ilc P.O. Box No. 490014 Dubai Industrial Park DUBAI United Arab Emirates

Your notice of Your reference Date 16-12-2022 27-01-2023

Analysis Report 22.06773.01

Required tests:

AS ISO 9239-1 (2003)

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

| Sample id | Information given by the client | Date of receipt |
|-----------|--|-----------------|
| T2225306 | 100% Solution Nylon carpet Tiles (MIMIC) | 16-12-2022 |

Kristina De Temmerman Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.









Analysis Report 22.06773.01 Date 27-01-2023 Page 2/3

T2225306 - 100% Solution Nylon carpet Tiles (MIMIC) **Reference:**

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test 24-01-2023

Standard used AS ISO 9239-1 (2003)

Deviation from the standard

23°C, relative humidity 50% Conditioning

Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate Fibre cement board - density (1800 \pm 200) kg/m³

Loose-laid Mounting

Specimens have not been cleaned

Joint At 25 cm and 75 cm





Radiant heat flux

| | Flame spread distance (cm) | | | Flame time | Heat flux kW/m ² | | |
|---------|----------------------------|-----|-----|------------|-----------------------------|---------|-------------|
| | 10 | 20 | 30 | Extin- | | 30 min* | Extin |
| | min | min | min | guish- | | | guishment** |
| | | | | ment | | | |
| Width | | | | | | | |
| #1 | 14 | 24 | 25 | 25 | 24 min 06 s | 8.4 | 8.4 |
| Length | | | | | | | |
| #1 | 15 | 24 | 25 | 25 | 26 min 57 s | 8.4 | 8.4 |
| #2 | 15 | 24 | 32 | 43 | 53 min 22 s | 6.9 | 4.8 |
| #3 | 15 | 25 | 33 | 44 | 63 min 59 s | 6.7 | 4.6 |
| Average | | | | | | 7.3 | 5.9 |

^{*} Heat flux at the time of 30 minutes

Smoke production: Light attenuation

| | Maximu | um (%) | Total (%.min) | | |
|---------|--------|--------------------------|---------------|--------------------------|--|
| | 30 min | Extin- guish- ment | 30 min | Extin- guish- ment | |
| Width | | | | | |
| #1 | 10 | 10 | 84 | 84 | |
| Length | | | | | |
| #1 | 10 | 10 | 74 | 74 | |
| #2 | 12 | 12 | 91 | 102 | |
| #3 | 13 | 13 | 94 | 117 | |
| Average | | | 86 | 98 | |

^{**} Heat flux at the time of flame extinguishment