

No. 1554686.4

(Please quote this number in all correspondence)

CLIENT:
Belgotex
25 Leslie Hills Drive
Riccarton, Christchurch

SAMPLE RECEIVED FROM:
Belgotex

Date Received: 10.2.25

Attn.: Geri Hansen

SAMPLE DESCRIPTION:
Grey cut pile carpet – Riverside Reserve
Nominal Composition – 100% Stainproof Solution Dyed Nylon
Nominal Yarn Weight – 1800 gsm

Client Order No.:

Client Reference:

1 of 2

ISO 9239.1: 2010, PART 1 – REACTION TO FIRE TESTS FOR FLOORINGS. DETERMINATION OF THE BURNING BEHAVIOUR USING A RADIANT HEAT SOURCE

Note: This test was sub-contracted (Test No. 25-000543).

CHF Value	1	2	3	Mean
Length (kW/m ²)	4.5	5.6	5.6	5.2
Width (kW/m ²)	5.6	-	-	-
HF – 30 Value				
Length (kW/m ²)	6.6	6.6	6.8	6.7
Width (kW/m ²)	5.6	-	-	-
Smoke Value				
Length (%.min)	175	162	168	168
Width (%.min)	181	-	-	-

Observations:

Melting

Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23 ±2°C and relative humidity of 50 ±5% for a minimum of 48 hours prior to testing.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

“THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED”

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.



C Judan
Key Technical Person

27/02/2025

No. 1554686.4

(Please quote this number in all correspondence)

CLIENT:
Belgotex
25 Leslie Hills Drive
Riccarton, Christchurch

SAMPLE RECEIVED FROM:
Belgotex

Date Received: 10.2.25


Attn.: Geri Hansen

SAMPLE DESCRIPTION:
Grey cut pile carpet – Riverside Reserve
Nominal Composition – 100% Stainproof Solution Dyed Nylon
Nominal Yarn Weight – 1800 gsm

Client Order No.:

Client Reference:

2 of 2



"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.


C Judan
Key Technical Person

27/02/2025



This document was created with the Win2PDF "Print to PDF" printer available at

<https://www.win2pdf.com>

This version of Win2PDF 10 is for evaluation and non-commercial use only.

Visit <https://www.win2pdf.com/trial/> for a 30 day trial license.

This page will not be added after purchasing Win2PDF.

<https://www.win2pdf.com/purchase/>