



REACTION TO FIRE CLASSIFICATION REPORT N° 2014/001-2

(English report of classification report N°2014/001-1)

According to EN 13501-1 (2007) + A1 (2013) – EN 13501-1 (2018)

Notification by the French Government to the European Commission
under n° NB 2401
Regulation (UE) n° 305/2011

Sponsor : BALSAN
Corbilly Arthon
36330 LE POINCONNET
FRANCE

Product name : Family group carpet tiles polyamide on bitumen backing

Description : Textile floor coverings (EN 1307 family)
(see detailed description in paragraph 2)

Date of issue : 11/04/2025 (update)

The indicated classification does not prejudice the conformity of marketed materials with the samples submitted to the tests and under no circumstances, this document should not be considered as type approval or certification of the product in the sense of the L 115-27 article of the consumption's code of the law.

*The reproduction of this classification report is only authorised in its integral form.
It comprises 6 pages*

1. Introduction

This classification report defines the classification assigned to the above-mentioned products in accordance with the procedures given in the NF EN 13501-1 standard: September 2007 & A1 (2013) – EN 13501 (2018).

2. Details of classified product**2.1. Product standard**

NF EN 14041 (2005): « Resilient, textile and laminate floor coverings - Essential characteristics.

2.2. Product description

Tufted carpet tile 100% polyamide on bitumen backing (EN 1307 family).

Tested loose laid over a fibre-cement board classified A1_{fl} or A2_{fl} with a density (1800 ± 200) kg/m³ and thickness (8 ± 2) mm.

Use surface : 100 % polyamide

Nominal mass per unit area : 3955 to 4920 g/m²

Nominal effective pile thickness : 0,6 to 5,8 mm

3. Test reports and tests results in support of this classification**3.1. Tests reports**

Name of laboratory	Name of sponsor	Test report N°	Test method
C.R.E.T.	BALSAN Corbilly Arthon 36330 LE POINCONNET FRANCE	RL 2025/164 (1-2) (11/04/2025)	EN ISO 9239-1 EN ISO 11925-2

Name of laboratory	Name of sponsor	Test report N°	Test method
C.R.E.T	BALSAN Corbilly Arthon 36330 LE POINCONNET FRANCE	RL 2020/685 (06/11/2020)	EN ISO 9239-1

Name of laboratory	Name of sponsor	Test report N°	Test method
C.R.E.T	BALSAN Corbilly Arthon 36330 LE POINCONNET FRANCE	RL 2022/545 (1-2) (29/08/2022)	EN ISO 9239-1 EN ISO 11925-2

3.2. Tests results

Classes of reaction to fire for textile floor coverings, classified without further testing.

Test method	The flooring « WINTER » meets the requirements of table 2 of the standard NF EN 14041 (2015) and is classified without further testing (CWFT)
EN ISO 11925-2	Classification E_{fl}

Test method	Product	Number of tests	Results	
			Parameters	Compliance parameters
EN ISO 11925-2	SERENITE DALLE (CRET report RL 2025/164-2)	6	$F_s \leq 150 \text{ mm}$	Compliant
Surface exposure-15 secondes			Ignition of the filter paper	Compliant

Test method	Product	Number of tests	Results	
			Parameters	Compliance parameters
EN ISO 11925-2	UP DOWN (CRET report RL 2022/545-2)	6	$F_s \leq 150 \text{ mm}$	Compliant
Surface exposure-15 secondes			Ignition of the filter paper	Compliant

Classification : E_n

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
EN ISO 9239-1	SERENITE DALLE (CRET report 2019/556-1)	3	Critical heat flux (kW/m ²)	8,7
			Smoke (% X min)	176,6

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
EN ISO 9239-1	WINTER (CRET report 2020/685)	3	Critical heat flux (kW/m ²)	8,3
			Smoke (% X min)	127,9

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
EN ISO 9239-1	UP DOWN (CRET report 2022/545-1)	3	Critical heat flux (kW/m ²)	8,1
			Smoke (% X min)	48,2

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1 :2007 & A1 (2013) – EN 13501-1 (2018).

4.2. Classification

Fire behaviour		Smoke production
B _{fl}	-	s1

Classification : B_{fl} – s1

4.3. Field of application

This classification is valid for the following end use applications :

Loose laid over fibre-cement A1_{fl} or A2_{fl} with a density $\geq 1350 \text{ kg/m}^3$.

This classification is valid for the following product parameters :

- A nominal mass per unit area of : 3955 to 4920 g/m²
- A nominal effective pile thickness of : 0,6 to 5,8 mm

The classification of the product family is valid for the following trademarks :

ALIZE
 AVENUE
 BATIK
 BOLERO
 BOLERO Planks
 BROOKLYN
 DELTA
 DESERT
 ENCRE DALLE
 FLOW
 FOREST
 FREEDOM
 GRAND HOTEL DALLE
 GROOVE
 IMPACT
 IMPRESSION
 INFINI COLORS
 INFINI COLORS Planks
 INFINI COLORS PI
 JUNGLE
 KARMA
 LAKE
 L480
 LANDSCAPE
 LOUVRE DALLE
 MAQUIS
 METROPOLITAN DISTRICT
 METROPOLITAN GRAFIK
 MEZZO
 MISTRAL
 MODULAR DESIGN 620 LOOP
 MODULAR DESIGN 650 VELOURS
 MODULAR DESIGN 1030 SAXONY
 MODULAR DESIGN 1240 LCL

NIRVANA
NUAGE – CIRRUS
NUAGE – STRATUS
ODEON
ORIGAMI
PILOTE²
PILOTE² Planks
PILOTE 3D
PROGRESSION
RAIN
RESONANCE
RIALTO DALLE
RIVER
ROCK
SAVANE
SEASONS LINES
SEASON LINES Planks
SERENITE DALLE
SERENITE DALLE LINES
SIMOUN
SIROCCO
SOHO
STEPPE
STONE AGE
STONE AGE PI
STREAM
SYDNEY DALLE
TAKE A WALK
TOP DESIGN BOLERO DALLE
TOUNDRA
TRACK
TRAMONTANE
TRUST
TRUST LINES
TRUST LINK
TRUST STRIPES
ULTRASOFT DALLE
ULTRASOFT Planks
UP DOWN
URBANIST
VOYAGER
WINTER
WINTER Planks
ZEPHYR

5. Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 of AVCP and CE marking under the Regulation 305/2011/EU of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of constructions products.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”

For the SARL C.R.E.T.
The Technical Director
Marc WELCOMME

A handwritten signature in black ink, appearing to be 'MW' followed by a stylized flourish.

End of the classification report