



Report VN710 132045.1 Classification Report



Applicant

EGETAEPER A/S
Industrivej Nord 25
7400-Herning
Denmark

Reference

Lenette Ormstrup

Application

Classification of burning behaviour according to EN 13501-1.

Test material

"PA-WT" (C_{fl}-s1)

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 8

Original Issue / Vienna 08.08.2017 / AA / 201

Authorised for Institute
Ing. Hannes Vittek

Contents

1	Order	2
1.1	Chronology	2
2	Introduction	2
3	Details of classified building product	2
3.1	General	2
3.2	Description of the building product	3
4	Test reports and test results for the proof of the classification	5
4.1	Test report	5
4.2	Test results	6
5	Classification and field of application	7
5.1	Reference for classification	7
5.2	Classification	7
5.3	Field of application	7
6	Limitations	7
6.1	Notice	7
7	Remarks	8

1 Order

1.1 Chronology

Date	Received	Order
09.02.2017	09.02.2017	Classification of burning behaviour according to EN 13501-1.

2 Introduction

This classification report defines the classification assigned to the building product group **“PA-WT” (C_{fl} – s1)** in accordance with the test methods fixed in EN 13501-1.

3 Details of classified building product

3.1 General

The building product group **“PA-WT” (C_{fl} – s1)** is defined as flooring, the classification is valid for the end use application described under point 5.3.

3.2 Description of the building product

The building product group **“PA-WT” (C_{fl} – s1)** is defined according EN 14041 as following.

Type	Textile floor coverings with pile according to EN 1307
Dimensions	Rolls
Manufacturing technique	Tufted
Surface structure	Cut pile
Backing	Woven Secondary Backing
Pile material	100% Polyamide
Total weight	2250 – 3550 g/m ²
Total thickness	7,0 – 15,5 mm
Pile weight	760 – 2000 g/m ²
Pile thickness	4,5 – 13,0 mm

Type	Textile floor coverings with pile according to EN 1307
Dimensions	Rolls
Manufacturing technique	Tufted
Surface structure	Loop pile
Backing	Woven Secondary Backing
Pile material	100% Polyamide
Total weight	2050 – 2750 g/m ²
Total thickness	5,0 – 8,0 mm
Pile weight	440 – 1100 g/m ²
Pile thickness	3,0 – 4,0 mm

Type	Textile floor coverings without pile according to EN 1307
Dimensions	Rolls
Manufacturing technique	Woven (flat woven)
Surface structure	Loop similar (plain, ribbed and structured)
Backing	Woven Secondary Backing
Pile material	100% Polyamide
Total weight	1800 – 2600 g/m ²
Total thickness	3,0 – 4,5 mm
Pile weight	345 – 700 g/m ²

The applicant of this classification report guarantees the observance of the instructions for building product groups according EN 14041 as well as the observance of the instructions of the product specification according to EN 1307.

The following articles are part of the building product group “PA-WT” (C_{fl} –s1).

Article	Surface Structure	Manu- facturing technique	Total weight [g/m ²]	Total thickness [mm]	Pile weight [g/m ²]	Pile thickness [mm]
Epoca Silky WT	Cut	Tufted	3050	11,5	1500	9,0
Epoca Texture WT	Cut	Tufted	2650	8,0	1100	5,5
Epoca Texture 2000 WT	Cut	Tufted	3550	15,5	2000	13,0
Epoca Twist WT	Cut	Tufted	2700	8,0	1100	5,5
Highline 1100 WT	Cut	Tufted	2550	8,0	1100	5,5
Highline 750 WT	Cut	Tufted	2250	7,0	760	4,5
Highline 910 WT	Cut	Tufted	2350	7,5	910	5,0
Ege Tuft 440 WT - Carre	Loop	Tufted	2050	5,5	440	3,0
Ege Tuft 950 WT	Loop	Tufted	2500	8,0	950	4,0
Epoca Chess WT	Loop	Tufted	2750	6,0	1100	3,0
Epoca Classic WT	Loop	Tufted	2350	6,5	590	4,0
Epoca Classic 1/10 WT	Loop	Tufted	2500	5,5	725	3,0
Epoca Frame WT	Loop	Tufted	2500	5,5	800	3,0
Epoca Ribs WT	Loop	Tufted	2100	5,0	750	3,0
Highline Loop e16 WT	Loop	Tufted	2100	6,5	850	3,0
Highline Loop WT	Loop	Tufted	2200	7,0	680	4,0
Una Tempo WT	Loop	Tufted	2200	5,5	500	3,0
Epoca Compact WT	Loop similar	Flat Woven	2600	4,0	700	--
Epoca Globe WT	Loop similar	Flat Woven	2350	4,0	700	--
Epoca Knit WT	Loop similar	Flat Woven	2100	4,0	560	--
Epoca Plait WT	Loop similar	Flat Woven	2400	4,0	700	--
Epoca Pro WT	Loop similar	Flat Woven	2450	4,0	700	--
Epoca Profile WT	Loop similar	Flat Woven	2350	3,5	625	--
Epoca Rasp WT	Loop similar	Flat Woven	2100	4,5	700	--
Epoca Stucture WT	Loop similar	Flat Woven	2400	4,5	700	--
Rawline WT	Loop similar	Flat Woven	1800	3,4	345	--
Una Casa WT	Loop similar	Flat Woven	2200	3,5	400	--
Una Micro WT	Loop similar	Flat Woven	2400	3,0	550	--

4 Test reports and test results for the proof of the classification

For building product groups preliminary trials with the heaviest/thickest and lightest/thinnest quality have to be carried out (for the most unfavourable case a complete test has to be carried out) respectively the test results of these "border-qualities" are used for the judgement. The classification is done according to the worst case ("Highline 750 WT", "Epoca Chess WT", "Una Micro WT").

4.1 Test report

Laboratory	DBI
Article	Highline 750 WT
Test report number	PF13187
Date of issue	2009-11-09
Applicant	Egetaepper A/S
Test methods	EN ISO 9239-1 and EN ISO 11925-2

Laboratory	DBI
Article	Epoca Chess WT
Test report number	PF12442w
Date of issue	2006-11-09
Applicant	Egetaepper A/S
Test methods	EN ISO 11925-2 and EN ISO 9239-1

Laboratory	DBI
Article	Una Micro WT
Test report number	PFA10625b
Date of issue	2014-11-11
Applicant	Egetaepper A/S
Test methods	EN ISO 11925-2 and EN ISO 9239-1

4.2 Test results

	Test results (Mean Value)	Number of tests
“Highline 750 WT”		
Ignitability, EN ISO 11925-2 Flame spread ≤ 150 mm	yes	6
Burning behaviour, EN ISO 9239-1 Critical radiant flux	6,0 kW/m²	3
Integral of smoke obscuration	44 %.min	3
“Epoca Chess WT”		
Ignitability, EN ISO 11925-2 Flame spread ≤ 150 mm	yes	6
Burning behaviour, EN ISO 9239-1 Critical radiant flux	5,3 kW/m²	3
Integral of smoke obscuration	385 %.min	3
“Una Micro WT”		
Ignitability, EN ISO 11925-2 Flame spread ≤ 150 mm	yes	6
Burning behaviour, EN ISO 9239-1 Critical radiant flux	6,0 kW/m²	3
Integral of smoke obscuration	140 %.min	3

5 Classification and field of application

5.1 Reference for classification

This classification has been carried out in accordance with EN 13501-1.

5.2 Classification

Due to the results of the tests carried out, the building product group **“PA-WT” (C_{fl} –s1)** can be classified as following.

Burning behaviour	Smoke emission
C _{fl}	s1
Classification C_{fl}-s1	

5.3 Field of application

The classification is valid for the building product group described in point 3 under the following end use conditions.

Application	Horizontal laid floor covering in form of rolls
Subfloors	Not burnable subfloors of euroclass A1 _{fl} or A2 _{fl} with a density of at least 1350 kg/m ³ .
Installation	glued
Adhesive	Polyacrylat-copolymer dispersion adhesive (“Ege 90RH” / “UZIN UZ 75”) Note: According to EN13501-1(a) the stated classification is valid for the tested floor covering together with the tested adhesive, as well as for all other adhesives of the same generic type as the tested adhesive.

6 Limitations

6.1 Notice

This classification document does not represent type permission or certifying the product.

If a building product should be CE marked according to system 3 of the attestation of conformity systems, the classification stated with this report is suitable as a basis for the declaration of the producer according to the attestation of conformity system 3, together with a CE marking in the context of the directive relating to construction products.

If the manufacturer plans a CE marking in connection with conformity system 3, he has to give an explanation, which has to be attached to the relevant documents. This explanation confirms, that there are no the specific materials, production processes or procedures (e.g. no additives of flame retarding materials, delimitation of organic components or additions of fillers), which are improving the burning behaviour to reach the obtained fire classification. As a consequence from this, the manufacturer drew the conclusion that the system 3 of the attestation of conformity systems is appropriate.

The testing laboratory therefore has played no role in the sampling procedure, although the testing laboratory keeps appropriate references from the manufacturer ready, in order to pursue the examined samples.

7 Remarks

Validity

There are no regulations concerning duration of validity in the individual test standards. As the results of the examinations refer only to the submitted and examined samples, the report is valid for these for an unlimited period. A period of validity specified as part of an expert evaluation is in the discretion of the consultant or the ÖTI.

The applicability of results and expert evaluations for materials not tested is in the responsibility of the applicant. Whereby an apportionment of results as well as any specified period of validity can only be done for identically constructed products and only as long as the product produced unchanged.

Possible national or international restrictions concerning the terms of usability of test and classification reports have to be considered; this is not the responsibility of the test laboratory.

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Quality management, Accreditation and Notification

All tests and services are performed under a quality management system according to EN ISO/IEC 17025 respectively EN ISO/IEC 17065.

The ÖTI is accredited as Testing Laboratory and Certification Body for products. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/nando/>). Accreditation as Testing Laboratory was provided by Akkreditierung Austria (bmwfw). The scope of accreditation is listed on www.bmwfw.gv.at/akkreditierung.

In this report individual non-accredited test procedures are marked with *.

According to the decree on the use of the accreditation mark ("AkkZV") the accreditation mark is only to be used by the accredited Conformity Assessment Body.

Application of the registration number of the Notified Body: As to personal protective equipment (PPE) the requirements of PSA-SV § 10, BGBl. Nr. 596/1994 as amended and article 13 of the Directive 89/686/EEC have to be kept. With construction products the application is only permitted within the declaration of performance for CE-marking.

Copyright and Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.

End of report