

**ATTAR TEST REPORT NUMBER: 14/8052.2**

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards.
Accredited for compliance with ISO/IEC 17025.
Accreditation Number: 2735

9 July 2014

Total Pages: 2**OIL-WET INCLINING PLATFORM SLIP RESISTANCE**

Job No: M14/8052

Prepared for:	Gerflor Australasia Pty Ltd 17 Cato Street HAWTHORN EAST VIC 3123	
Attention:	Jutta Fronert	
Test Site:	ATTAR, Unit 1, 64 Bridge Road, Keysborough.	
Test Date:	4 July 2014	
Manufacturer:	Gerflor	
Test Specimen, Size & Quantity:	Taralay Premium Compact (P2), 100x50 cm, 1 off supplied. Refer to Figure 1.	
Sampling & Direction of Testing:	Sampling conducted by client. Test direction not applicable.	
Test Personnel:	Daniel King & Darren Cram	
Preparation:	Washed with water and pH Neutral detergent, rinsed then dried.	
Joint Width:	N/A	
Air Temperature:	22°C	
Test Standard:	AS 4586 - 2013 Slip resistance classification of new pedestrian surface materials – Appendix D.	
Surface Structure :	Smooth	
Test Shoes:	Lupos Picasso	
Classification Criteria: (TABLE 5 in AS 4586 - 2013)	Classification	Angle, degrees
	No Classification	<6
	R9	≥6<10
	R10	≥10<19
	R11	≥19<27
	R12	≥27<35
	R13	≥35
Displacement Space:	Not Measured	
Displacement Space Assessment Group:	N/A	
Corrected Mean Overall Acceptance Angle (rounded down to the nearest degree):	11°	
Classification:	R10	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTAR

Daniel King BEng (mat) Hons,
Materials and Testing Engineer
Approved Signatory

This report may not be reproduced except in its entirety.

Page 1 of 2