



PTV—Slip potential on Kährs Life

Test made with an portable "skid-resistance" tester from Stanley London. Rubber used is a CEN rubber. Test performed according to SS-EN_13036-4_2011. Test object was Kährs Life LTCLRW3008-193. Two different boards both acclimatized in 23°C / 50% relative humidity. Test was made dry.

Result was Low Slip Potential on "Slipalert" graph.

