Decochoc

Description	Decochoc Protection and Covering Panel
Thickness	2.0mm +/- 0.15mm
Width	1300mm
Length	3000mm
Weight	2800g/m² +/-200
Density	1.40g/cm³
Hardness	75ShD
Stabilization	CaZn
Surface	Textured with Optimixt Embossment
Thermal Conductivity	0.17 W/(m.K) (DIN 52612)
Fire Rating	B-s2,d0 (EN 13501-1)
Chemicals resistance	Anios compliant H2O2 compliant
Decontamination of surface (radionuclide)	Excellent (ISO 8690)
Anti-bacterial activity (2) (S. aureus – S. pyogenes)	> 99% inhibits growth (ISO 22196)
Migration of specific metals	<2 (EN12149-A)
Vinyl Chloride	Non detectable (EN12149-B)
Puncture impact	> 15J (EN ISO 6603-1)
Formaldehyde	Non detectable (EN12149-C)
Impact Resistance Charpy	> 30KJ/m² (ISO 179-1)
Chemical Resistance	OK (EN ISO 26987)
Indoor Climate	TVOC after 28 days < 15µg/m3 (ISO 16000-6) A+ Emissions, Greenguard Gold label
Installation	Please see our website for installation instructions. NB: If the recommended installation is not followed, claims will not be accepted.
Environmental	100% REACH Compliant 100% Recyclable

- For samples, range and warranty details please contact us on 0800 377 753 or belgotex.co.nz
- Chair pads are recommended under office chairs with roller castors to preserve appearance retention and to avoid premature and accelerated wear.
- Specifications are based on averages from manufacturing processes and may vary within normal industry tolerances: Width ±3mm, Pile Weight ±5%.
- Material supply and/or manufacturing processes may necessitate specification changes without notice. Such variations do not affect product performance.

Belgotex®

A world of perfect choices_